



TCC-6000A/6070B (70 Shore D)

POLYURETHANE CASTING
SYSTEM

PRODUCT BULLETIN



www.CASSpolymers.com
31200 Stephenson Hwy

800.344.7776
Madison Heights MI 48071

TCC@CASSpolymers.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

TCC-6000A/6070B is a two-component urethane casting system designed to give a 70 Shore D hardness material with exceptional toughness. This long work life casting system offers outstanding performance properties including high strength, low shrinkage and easy processing. In many applications parts can be demolded several hours after casting. In complex parts or very thin sections, castings may require 9 – 16 hours before demolding; and in very demanding applications, an additional cure of 3 or 4 days at room temperature may be required before use. Ultimate properties are reached after 7 days at room temperature or by curing for 9 - 16 hours at room temperature, then post curing for a minimum of 6 hours at 160°F (71°C).

Typical Applications Include: Long Lasting Molds • Industrial Wheels • Drop Hammer Faces • Washers • Gaskets • Foundry Patterns • Core Box Linings

HANDLING CHARACTERISTICS @ 25°C/77°F

Mix Ratio (parts by weight).....	Resin TCC-6000A/Hardener TCC-6070B.....	100A/35B
Pot Life (150 gram mass).....		20 - 25 minutes
Initial Mixed Viscosity		2,000 cps
Mixed Color		Amber
Shelf Life Resin/Hardener (in original unopened containers)		2 years

TYPICAL PHYSICAL PROPERTIES

Hardness Buildup (150 gram mass @ 77°F)	after 24 hours	63 - 68 Shore D
	after 48 hours	67 - 73 Shore D
	after 72 hours	67 - 73 Shore D
Cured Specific Gravity		1.09
Tensile Strength		4,000 psi
Elongation		150%
Linear Shrinkage		<0.004 in/in
Notched Izod Impact Strength.....		4.83 ft lbs/in
Tear Strength, split.....		100 pli
Tear Strength, Die "C" graves.....		650 pli
Heat Deflection Temperature (66 psi).....		135°F (57°C)

MIXING PROCEDURE

Use an accurate gram scale to properly weigh and proportion A/B components into a straight sided metal or plastic container for mixing. Paper or wax lined mixing containers can contain moisture and contaminate material. Next, use a metal or plastic mixing spatula to gently but thoroughly blend resin and hardener together. Once the urethane appears to be well mixed, pour into a second container and continue to mix for another two to three minutes. This procedure eliminates the possibility of any unmixed material being poured into the final cast. Vacuum degass mixture before casting to produce an air free part.

Continued on next page

MOLDS

Use TCC Casting Urethane systems for mold construction. You can choose from the TCC-5000 series of flexible Shore 'A' 50-95 systems or TCC-6000 series of semi-rigid Shore 'D' 60-75 systems. Urethane molds should be fully cured before use and require the application of mold release agent such as MR #10 high gloss mold release. MR #10 is a low viscosity, water clear, non-transferable polymer mold release that can be applied by brush or non-aerosol sprayer. Other mold release systems are available.

TCC CASTING URETHANES	
Flexible Tooling Elastomers	
TCC-5000A/5050B - 50 Shore A	TCC-5000A/5060B - 60 Shore A
TCC-5000A/5070B - 70 Shore A	TCC-5000A/5080B - 80 Shore A
TCC-5000A/5081B - 80 Shore A - long working life	
TCC-5000A/5090B - 90 Shore A	TCC-5000A/5095B - 95 Shore A
Rigid Tooling Elastomers	
TCC-6000A/6061B - 60 Shore D	TCC-6000A/6065B - 65 Shore D
TCC-6060A/B - 60 Shore D - short working life	
TCC-6000A/6070B - 70 Shore D	TCC-6075A/6075B - 75 Shore D
Pronto Parts for Rapid Prototyping	
TCC-8020A/TCC-8021B - 75 Shore D	TCC-8040A/B - 80 Shore D - High Temp
Crystal Clear Casting System	
TCC-6080 A/B - 80 Shore D	

SANITARY PRECAUTIONS

Do not take internally. Avoid prolonged breathing of vapors. Work in a well ventilated area. Avoid skin contact. Protective gloves should be worn. If contact occurs: wash skin with soap and water. Avoid eye contact. If contact occurs: rinse well with water for 15 minutes, contact physician.

STORAGE AND HANDLING

Store closed containers at 65°F-85°F. Partially used containers must be flushed with dry nitrogen and resealed. Materials are sensitive to moisture contamination.

TCC-6000A/6070B Tech/Revised 11/17/10
Supercedes 4/16/10

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.